

ALPHA AGR40 alpha-plaster

Properties Alpha AGR40 is an alpha hemihydrate plaster made of natural materials with

special process.

Where to use Alpha AGR40 is primarily used as a basic substance for gypsum-bearing

building material.

Technical data Mixing ratio (g/100ml): 270-320

Water-gypsum ratio: 0,36-0,34
Beginning of setting (minutes): > 2
End of setting (minutes): < 20
Hemihydrate (%): > 90

Grading (%):

R 32 µm 35-45

Flexural strength $(7d - N/mm^2)$: > 10 Compressive strength $(7d - N/mm^2)$: > 45

MSZ EN: 13279
Declaration of performance number: 104007
Tariff heading: 25202000

Packaging Available in 25 kg multilayered paper bags, 40 bags/pallet, in heat-shrink

wrapping Storage In covered, dry place, for approximately 6 months from the

date of manufacture, in unopened bags

Manufacturer CASEA GmbH., Germany

Distributor Széria-Trans Kereskedelmi és Szolgáltató Kft.

H-1116 Budapest, Adony u. 7, Phone: +36-1-466-7758 H-5300 Karcag, Tilalmasi út 1, Phone: +36-59-311-333

This data sheet was prepared to the best of our understanding. The data contained therein reflect our latest technical knowledge and observations. However, we shall not be held liable for the statutory provision of contents. Users shall honour any patent rights, and shall comply with the applicable laws and regulations at their own responsibility.