

gypsum-lime

## GYPSUM MACHINE PLASTER (GÉPI VAKOLAT)

Ready-mixed render for machine application made of gypsum, hydrated lime and sand, with admixtures designed to improve its properties.

Where to use	Render, smoothing and topcoat render for all interior areas. Not suitable for industrial areas subject to damp and moisture. If used as a render it is suitable for carrying the topcoat render (lightweight render) and tiling. If used as second coat, it can be painted and wallpapered. Do not mix with any foreign material.
Application	Can be spread with all known plastering machines. <u>Use as a render coat:</u> Apply and spread evenly, then repeat the process when it starts setting. <u>Use as a smoothing, topcoat render:</u> After spreading, use a slightly wet sponge trowel to dampen the rendered surface, and apply a layer of topcoat.
Substrate requirement	Suitable for all types of walls, concrete and contact mortar surfaces. If substrate is unstable metal reinforcements and at least a 10 mm thick layer of mortar is required. The substrate must be clean and dry, remove all loose and peeling particles, dust, contamination and detached layers of materials. Use a primer for concrete substrates, in highly absorbent areas. For new concrete surfaces, residual moisture must be below 3%.
Safety advice	Irritating to the skin and eyes when mixed with water. Avoid contact with the skin and eyes. In the event of contact with the skin, rinse immediately with plenty of water, in the event of contact with the eyes seek medical advice.
Technical data	Mortar class: P IVc, DIN 18550 Compressive strength: > 2.0 N/mm <sup>2</sup> Average thickness: 10 mm Consumption: approx. 10 kg/m <sup>2</sup> /1 cm Water requirement: approx. 13 litre/30 kg
Packaging	Available in 30 kg paper bags, 35 bags/pallet, in heat-shrink wrapping Bulk, in silo
Storage	In a covered place, in dry conditions, for approximately 6 months from the date of manufacture, in unopened bags
Manufacturer	CASEA GmbH., Germany
Distributor	Széria-Trans Kereskedelmi és Szolgáltató Kft. H-1116 Budapest, Adony u. 7, Phone: +36-1-466-7758 H-5300 Karcag, Tilalmasi út 1, Phone: +36-59-311-333